

## Technical Information

Version: 1.0

Date of issue: 17.01.2017

### Purios 2500 B – Side

#### GENERAL INFORMATION

Two component system for producing rigid polyurethane foam. No blowing agent lean the ozone layer containing.

PRODUCT CHARACTERISTIC			
	Component B	Component A	Standard
Viscosity 77°F [cps]	400 – 750	170 – 230	ASTM D 2196
Specyfif gravity 77°F	1.10 – 1.20	1.22 – 1.24	ASTM D1638
Mixing ratio (by volume)	100	100	
FOAMING CHARACTERISTIC			
Start time [s]	4 – 7		
Gelation time [s]	9 – 13		

\*components temperature in foaming test 104 – 122 °F

#### APPLICATION

In the formulation of thermal-insulating polyurethane spraying rigid foam (ceilings, walls, roofs, floors and floorings).

**Component B** (Purios 2500) mixture of polyols with additives.

**Component A** (Purios A) polymeric diphenylmethane 4, 4' diisocyanate.

FOAM PROPERTIES		
Thermal resistance (R-value at 1 inch)	6,86 hft <sup>2</sup> °F/Btu	ASTM C 518
Density foam in finished product	3,12 lb/ft <sup>3</sup>	ASTM D 1622
Compressive strength at 10 % strain	≥ 55 psi	ASTM D 1621
Closed cells content	min. 90 %	ASTM D 6226

**Note:** The process for the preparation of the foam takes place with the release of heat, and therefore it depends on the external conditions, the lower the temperature of the raw materials of the substrate or the environment, the lower is the degree of expansion (foaming). Foam properties becomes full after 48 hours.

#### CONDITIONS OF STORAGE AND TRANSPORT

Optimal storage temperature is 59 – 73,4 °F. Raw materials should be stored in dry and closed rooms. Both components must be protected against moisture from the air. Shelf life in original manufacturer's packaging, stored at the recommended conditions is 6 months from the date of manufacture.

According to RID / ADR, both components are not hazardous materials.

Notice: Encompassed dates in this technical information obtained in of the model conditions.

During the work in other possible conditions it's possible to obtain differ results from given.

This information and our technical advice - whether verbal, in writing or by way of trials - are given in good faith but without warranty, and this also applies where proprietary rights of third parties are involved. Our advice does not release you from the obligation to verify the information currently provided - especially that contained in our safety data and technical information sheets - and to test our products as to their suitability for the intended processes and uses. The application, use and processing of our products and the products manufactured by you on the basis of our technical advice are beyond our control and, therefore, entirely your own responsibility. Our products are sold in accordance with the current version of our General Terms and Conditions of Sale.